










Alligator Clay

Updated: 12/10/2009

	MC#	Description	Stocked	
Earthenware		101 Smooth bright white low-fire body. Very plastic with excellent mechanical working properties. Recommended firing range is cone 07-03 . This is the best throwing white earthenware we have ever found.	12	All clay is sold in 50 lb boxes at \$29.98 per box.
		107 A low fire, red terra cotta clay. At cone 06 this clay gives a light orange color, and at cone 2 will be dark red brown. This is a smooth, plastic red clay, ideal for wheel work.	8	
	Gumbo	110 Gumbo clay is the result of purging our mixer between batches of different clay. A guaranteed surprise in every bag, with some of this and some of that. Suitable for cone 04 firing.	5	
		138 One of the best clay bodies we've ever developed. No brag, just fact. A wonderful blend of stoneware and fireclays that produce a Raku clay that is a joy to throw. Fires to cone 06 - 10 .	5	
Mid-Range Stoneware		212 This is a relatively smooth, stoneware type clay, which may be fired at cone 4 - 6 . When fired this clay is light brown with darker speckles. Good clay for throwing or sculpture.	5	
		221 A reddish, mid-range clay. This clay fires to a light orange-brown hue, and may be fired from cone 4 - 6 . This clay has 3% grog but is quite smooth, making it great for wheel throwing or sculpting.	5	
		241 Mid-range stoneware with a warm wheat color in oxidation. Smooth clay, good for throwing or handbuilding. Fires at cone 4 - 6 .	5	
		250 Chocolate brown at cone 6 oxidation. Oxidation fire only.	5	
	No Chip Sample At This Time	285 A light brown stoneware with grog. Excellent handbuilding and sculpting clay but not too groggy to throw with. Warm light brown like coffee milk. Fires cone 4 - 6 .	5	
Hi-Fire Stoneware		305 Super sculpture body that fires to cone 6 - 10 . 30% medium and fine grog.	5	
		311 Beautiful dark brown stoneware. Chocolate brown in reduction. Fires cone 6 - 10 . Nice orange-brown at cone 6 oxidation.	5	